

HIKRA®

solar cables
part of **HIS** CONNECT™

HIKRA® PLUS DB EN50618 (H1Z2Z2-K) IEC62930

DATA SHEET

IN FOCUS IS THE PLANT REVENUE IN OPERATION OUR SOLAR CABLES

- Higher water resistance - direct burial
- CPR compliant EN50575
- Higher mechanical stability
- 25 years expected lifetime
- Meter marking





Type Approved
Safety
Regular Production
Surveillance



www.tuv.com
ID 1111221037

Construction	
Strand construction	Tin-plated copper strand (electrolytic copper), fine wire acc. IEC 60228 Class 5
Insulation	Cross-linked Polyolefin; Shore hardness D 32; Minimum wall thickness acc. EN 50618 table 1
Outer Sheath	Cross-linked special compound XLPO; Shore hardness D 36; Minimum wall thickness acc. EN 50618 table 1
Colour	Sheath: black, red, blue; Insulation: clear – naturally colored
Marking	HIKRA PLUS DB cross-section EN 50618 H1Z2Z2-K 62930 IEC 131 CE R601480037 Chargen No Meter marking
Standards	EN50618 (H1Z2Z2-K) TÜV R60148037: IEC62930 131

Technical characteristics	
Nominal voltage	1,5kV DC and 1,0kV AC
Maximum permitted operating voltage	1,8kV DC (additional internal examination 2,0kV DC)
Voltage test on complete cable	6,5kV AC / 15kV DC (5 minutes water bath, 20±5°C)
Current carrying capacity	See document „Current rating – HIKRA® Solar Cable“ November 2013
Short-circuit-temperature	250° C/5s

Material properties	
UV stability	Tensile strength and ultimate-elongation after 720 h (360 cycles) ≥ 70% of initial values; EN 50289-4-17 acc. Method A; EN ISO 4892-1 (2000) and EN ISO 4892-2 (2006)
Ozone resistance	72h, relative humidity 55±5%, Temperature 40±2°C (EN 50396 Method B; Ozone concentration [200±50]x10 ⁻⁶)
Insulation resistance	Insulation resistance in water bath, each 2h at +90°C and 2h at 20°C (Limit values acc. EN 50618 Table 1)
Dynamic penetration test	Spring-steel-needle through insulation or sheath (EN50618 Annex D)
Direct burial	Long-term water immersion at 90°C, duration 12 weeks; Insulation resistance ≥ 3GΩ (additional internal examination acc. UL44 cl. 5.4 & UL2556 6.4.4.2.1)
Crushing- and impact-resistance	Impact-Resistance UL 854.23 and Crushing-Resistance UL 854.24 (internal examination)
Sheath resistance against acid and alkaline	168h at 23°C in N-Oxal acid and N-Sodium hydroxide (EN 60811-404); ammoniac-resistant
Behaviour in case of fire	Flame-retardant acc. EN 60332-1-2 Annex A, low smoke emission (EN 61034,-2)
CPR-Performance	Dca; Fire behavior EN50575
Halogen-free	EN 50525-1, Annex B
Cold impact test	EN 60811-506, EN 50618 Annex C.1 at -40°C
Cold bending test	-40±2°C, 16h (EN 60811-505)
Damp heat test	Duration 1000h at 90°C and min. 85% relative humidity (EN 60068-2-78)
Minimum bending radius flexible / fixed	10x cable diameter 4x cable diameter

Temperature range	
Temperature	Ambient temperature: -40° C to +90°C; Maximum conductor temperature: +120° C
Maximal storage temperature	+40°C
Minimum temperature for installation	-25°C

Order number		Cross-section mm ²	Construction n x max-Ø (mm)	Max. Resistance (Ω/km)	External diameter (+/- 0,2 mm)	Copper index kg/km	Approx. Weight kg/km
black	red						
747455	747456	1 x 4.0	56 x 0.31	5.09	5.5	38.4	56.0
747457	747458	1 x 6.0	80 x 0.31	3.39	6.0	57.6	75.0
747459	747460	1 x 10.0	80 x 0.41	1.95	7.1	96.0	115.0

www.his-solar.com

Headquarter Germany

France

Spain

Turkey

HIS Renewables GmbH
Siemensstraße 4
64760 Oberzent

HIS Renouvelables SARL
48, rue Claude Balbastre
34070 Montpellier

HIS Soluciones de Sistemas Solares S.L.
Avenida de Brasil 17
Madrid 28020

HIS Solar Sistemleri A.Ş
Alsancak Mah. 1479 Sk. N15
K3 D12 35220 Konak - İzmir

T +49 6068 9314 430
E sales@his-solar.com

T +33 4 67 27 68 20
E info.fr@his-solar.com

T +34 916 620 493
E info.es@his-solar.com

T +90 232 422 09 31
E info.tr@his-solar.com